

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 730 937 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

11.09.1996 Bulletin 1996/37

(51) Int. Cl.⁶: B29C 45/02, H01L 21/56,
B29C 33/68

(21) Application number: 95308258.3

(22) Date of filing: 17.11.1995

(84) Designated Contracting States:
CH DE FR GB IE LI NL

(30) Priority: 21.11.1994 JP 286934/94
21.11.1994 JP 286937/94
21.11.1994 JP 286944/94
29.11.1994 JP 294762/94
20.02.1995 JP 30353/95

(71) Applicant: APIC YAMADA CORPORATION
Hanishina-gun, Nagano 389-08 (JP)


(72) Inventor: Miyajima, Fumio,
c/o Apic Yamada Corp.
Hanishina-gun, Nagano 389-08 (JP)

(74) Representative: Sanderson, Michael John et al
MEWBURN ELLIS
York House
23 Kingsway
London WC2B 6HP (GB)

(54) A resin molding machine with release film

(57) A resin moulding machine includes moulding dies (10a, 10b) having moulding sections including cavities (21), the moulding dies (10a, 10b) being capable of clamping a member (20) to be moulded. A pot (12) pressurizes and sends resin melt to the cavities (21), while a fixing mechanism fixes release film (30), which is capable of easily peeling off from the moulding dies (10a, 10b) and from the resin for moulding, on inner faces of the moulding sections and clamping faces by sucking air.

FIG.1



EP 0 730 937 A1

Description

The present invention relates to a resin molding machine, a method of resin molding and release film for the machine and the method.

A conventional transfer molding machine is shown in Fig. 44. In the conventional machine, a member to be molded is clamped by an upper die 10a and a lower die 10b, then resin is filled into cavities to mold the member to be molded. The resin sent from a pot 12 directly contacts inner faces of molding sections of the dies 10a and 10b, a runner and a gate, so the dies 10a and 10b must have enough abrasion-proof ability and durability. The molding dies 10a and 10b are usually made of steel and heat treatment, surface treatment, etc. are executed.

In the conventional molding machine, solidified resin is stuck in the molding sections, etc., so there are provided ejector pins in the molding dies. And to remove the solidified resin on the molding dies, a cleaning step is required for each molding work.

Generally, thermosetting resin, e.g., epoxy resin, phenolic resin, is used. Thus, the molding dies must be heated to prescribed temperature, so that there are heaters in base sections of the molding dies. In the conventional molding machine, the resin directly contacts the molding dies as described above, heat can be directly exchanged between the resin and the dies, so that resin solidification can be accelerated and molding cycle time can be shortened.

However, the molding dies must have prescribed durability, so it is difficult to machine a hard material so as to make the dies. Furthermore, the ejector pins must be assembled in the dies, so the dies must have a complex structure. Due to the hard material and the complex structure, it is difficult to make the molding dies.

It would be desirable to be able to provide a resin molding machine having molding dies, which have simple structures and which can be easily made, and to provide a method of resin molding using release film, which is capable of employing various materials as a material for the molding dies, and the release film for the method and the machine.

According to one aspect of the present invention there is provided a resin molding machine comprising:

molding dies having molding sections including cavities, the molding dies being capable of clamping a member to be molded;

a pot for pressurizing resin melt to send the same to the cavities; and

a fixing mechanism for fixing release film, which is capable of easily peeling off from the molding dies and resin for molding, on inner faces of the molding sections and clamping faces, which are peripheral faces of the molding sections, the fixing mechanism fixing the release film by sucking air.

The resin molding machine may further comprises an air sucking mechanism for sucking air, and the fixing mechanism may comprises: a sucking air path whose one end is opened in the clamping end, and whose the

other end is connected to the air sucking mechanism; and a cavity air path whose one end is opened in the molding section, and whose the other end is connected to the air sucking mechanism.

In the resin molding machine, the cavities may be formed by fitting cavity pieces in attachment holes, which are formed in base sections of the molding dies, and the cavity air path may be a gap between an inner face of the attachment hole and an outer side face of the cavity piece.

In the resin molding machine, the molding sections may be made of a material whose heat conductivity is different from that of base sections of the molding dies, and the molding sections may be fitted in the base sections. And the cavity pieces may be made of a material whose heat conductivity is different from that of the base sections of the molding dies.

And the resin molding machine may further comprises a stopper block being provided to one of the molding dies, the stopper block defining a separation between the molding dies when the molding dies clamp the member to be molded. In this case, precise molding can be executed.

Secondarily, the a resin molding machine of the present invention comprises:

molding dies having molding sections including cavities, the molding dies being capable of clamping a member to be molded;

a pot for pressurizing resin melt to send the same to the cavities;

sucking means for sucking the member to be molded to fix, the sucking means being provided in one of the molding dies; and

a fixing mechanism for fixing release film, which is capable of easily peeling off from the molding dies and resin for molding, on inner faces of the molding sections and clamping faces, which are peripheral faces of the molding sections, the fixing mechanism being provided in one of the molding dies which is the opposite die to the die having the sucking means, the fixing mechanism fixing the release film by sucking air. By this structure, one side-molded products can be molded easily.

In the resin molding machine, an inner shape of the pot may be formed into a female-tapered shape in which diameter is made greater toward front open end, whereby wrapped resin can be easily supplied into the pot.

According to a further aspect of the present invention, there is provided a method of resin molding comprising the steps of:

clamping a member to be molded by molding dies having molding sections including cavities;

pressurizing resin melt by a pot so as to send the resin to the cavities;

fixing release film, which is capable of easily peeling off from the molding dies and resin for molding, on inner faces of the molding sections and clamping faces, which are peripheral faces of the molding sec-

tions, by a fixing mechanism for fixing the release film by sucking air; and

clamping the member to be molded by the molding dies together with the release film.

In the method, resin supplied into the pot may be tightly wrapped with wrapping film, and an edge of the wrapping film, which is overflowed from the pot, is overlapped with an edge of the release film in a resin path connecting the pot and the cavity, whereby sticking resin onto the dies can be prevented.

And the edge of the wrapping film, which has been set in the pot, may be coincided with a border between the cavity and a gate, whereby sticking resin onto the molded product can be prevented.

Further, in the method, the member to be molded may be a dam-barless lead frame. And the member to be molded may be a lead frame having a gate window, which is an opening section corresponding to a gate.

The release film of the present invention, which is fixed on inner faces of molding sections of molding dies and clamping faces thereof, which are peripheral faces of the molding sections, by sucking air,

characterized in that,

a transferring layer, which is capable of being transferred onto a surface of resin molded, is provided on a surface of the release film.

Embodiments of the present invention will now be described by way of examples and with reference to the accompanying drawings, in which:

Fig. 1 is a sectional view of a resin molding machine of First Embodiment;

Fig. 2 is an explanation view showing planar arrangement of cavity pieces of a molding die, release film, etc.;

Fig. 3 is an explanation view showing arrangement of wrapped resin, a member to be molded and the release film;

Fig. 4 is a perspective view of the wrapped resin;

Fig. 5 is an explanation view showing a method of setting the wrapping resin into the molding die by a jig;

Fig. 6 is an explanation view showing a sucking hole in a lower die;

Fig. 7 is a sectional view showing a state of sticking resin onto a lead frame;

Fig. 8 is an explanation view showing arrangement of wrapping film having an extended section;

Fig. 9 is an explanation view showing arrangement of wrapping film having no extended section;

Fig. 10 is a sectional view an upper die and a lower die having gates respectively;

Fig. 11A is a plan view showing a state of assembling the cavity piece;

Fig. 11B is a sectional view showing a state of assembling the cavity piece;

Fig. 12A is a plan view showing a state of assembling the cavity piece;

Fig. 12B is a sectional view showing a state of assembling the cavity piece;

Fig. 13A is a plan view showing a state of assembling the cavity piece;

Fig. 13B is a sectional view showing a state of assembling the cavity piece;

Fig. 14A is a plan view showing a state of assembling the cavity piece;

Fig. 14B is a sectional view showing a state of assembling the cavity piece;

Fig. 15A is a plan view showing a state of assembling the cavity piece;

Fig. 15B is a sectional view showing a state of assembling the cavity piece;

Fig. 16A is a plan view showing a molding die in which one end of a cavity air path is opened at a position separate away from one corner of the cavity, at which a gate is connected;

Fig. 16b is a sectional view showing a molding die in which one end of a cavity air path is opened at a position separate away from one corner of the cavity, at which a gate is connected;

Fig. 17A is a plan view showing a molding die in which one end of a cavity air path is opened at a center of the cavity, wherein the release film is sucked;

Fig. 17B is a sectional view showing a molding die in which one end of a cavity air path is opened at a center of the cavity, wherein the release film is sucked;

Fig. 18A is a plan view showing a state of filling resin into the cavity;

Fig. 18B is a plan view showing a state of filling resin into the cavity of the conventional machine;

Fig. 19A is a sectional view showing a method of assembling the cavity piece;

Fig. 19B is a sectional view showing a method of assembling the cavity piece;

Fig. 20 is an sectional view showing a method of assembling the cavity piece;

Fig. 21A is a plan view showing an integrated type molding die;

Fig. 21B is a sectional view showing the integrated type molding die;

Fig. 22 is a graph showing action of the release film;

Fig. 23 is an explanation view showing a resin molding method using the release film having fine holes;

Fig. 24 is a sectional view of the molding dies in which members, whose heat conductivity is different from that of the molding dies, are assembled;

Fig. 25 is a sectional view of the molding machine in which gates are provided in the upper die;

Fig. 26 is a plan view of the release film having a transferring layer;

Fig. 27 is a sectional view showing a molding method using the release film having the transferring layer;

Fig. 28 is a sectional view showing a molding method using BGA as the transferring layer;

Fig. 29 is an explanation view showing a molding method for a dam-barless lead frame;

Fig. 30 is a sectional view showing a pot and a plunger;

Fig. 31 is a sectional view showing a state of filling the resin into the cavities;

Fig. 32 is a sectional view showing another pot and plunger;

Fig. 33 is a sectional view showing a state of filling the resin into the cavities;

Fig. 34 is a sectional view showing another plunger;

Fig. 35 is a sectional view of a one side molding machine;

Fig. 36 is a sectional view of an upper die of the one side molding machine;

Fig. 37 is an explanation view showing planar arrangement of sucking air paths in the upper die of the one side molding machine;

Fig. 38 is an explanation view showing a method of setting a substrate and the release film onto the die;

Fig. 39 is an explanation view showing a method of setting the substrate and the release film onto the die;

Fig. 40 is an explanation view showing a method of setting the substrate and the release film onto the die;

Fig. 41 is a sectional view showing a state of closing the molding dies;

Fig. 42 is a sectional view showing another state of closing the molding dies;

Fig. 43 is a sectional view of a molding machine for chip-size packages; and

Fig. 44 is a sectional view of the conventional resin molding machine.

(First Embodiment)

Fig. 1 shows a resin molding machine using release film of First Embodiment. In Fig. 1, the left side of the center line shows a state of clamping a lead frame 20, which is a member to be molded; the right side thereof shows a state of filling resin into a cavity 21.

An upper die 10a and a lower die 10b have cavities. In the present embodiment, bottoms of the cavities are formed by fitting cavity pieces 22a and 22b in the dies 10a and 10b. Base sections of the dies 10a and 10b are made of steel; the cavity pieces 22a and 22b are made of a material having high heat conductivity, e.g., copper, aluminum. The cavity pieces 22a and 22b, of course, may be made of steel.

Fig. 2 shows arrangement of the cavity pieces 22b in the lower die 10b. The cavity pieces 22b are formed like blocks. Through-holes for fitting the cavity pieces 22a and 22b are bored in the base sections of the molding dies 10a and 10b. The cavity pieces 22a and 22b are respectively inserted in the through-holes, and they are fixed to plates 24a and 24b by screws.

There is provided a cull piece 26 in the upper die 10a. The cull piece 26 is made of a material different from the base section of the upper die 10a. The cull piece 26 is positioned to face a pot 12. The cull piece 26 is fixed to the plate 24a. The cull piece 26 too may be made of the material having high heat conductivity, e.g., copper, aluminum.

Since the cavity pieces 22a and 22b and the cull piece 26 are made of the material having high heat conductivity, heat exchange between resin filled in the cavities and the molding dies 10a and 10b can be effectively executed, so that resin solidification can be accelerated.

To heat the dies 10a and 10b, the dies 10a and 10b are fixed to the plate 24a and 24b together with heat block 25a and 25b in which heaters 28 are provided. In the present embodiment, heaters 23 are further provided in the cavity pieces 22a and 22b and the cull piece 26, with this structure, the cavity pieces 22a and 22b and the cull piece 26 can be heated effectively. Thermosensors, e.g., thermocouples, thermostats, are provided to the heaters or the pieces 22a, 22b and 26.

Generally, copper and aluminum cannot be used for the molding dies. But, by using release film, they can be used for the molding dies other than the base sections. In the method of resin molding using the release film, parts of the molding dies in which resin directly contacts the molding dies are covered with the release film to prevent the resin from contacting the molding dies.

In the present embodiment, the resin molding is executed by the steps of: feeding a sheet of the release film onto parting faces of the dies 10a and 10b so as to cover molding sections of the dies 10a and 10b; setting a member to be molded on the die 10b; clamping the member to be molded by the dies 10a and 10b; and filling the resin melt into the cavities to mold. After molding, the molded product is taken out independently or together with the release film by a proper mechanism.

The release film is required to resist molding temperature of the dies. And it is also required to be easily peeled off from the dies and the molded products. Thus, FEP sheet film, glass cloth in which fluoric resin is impregnated, PET sheet film, ETFE sheet film, polyvinylidene chloride, etc. can be employed as the release film.

In the left side of Fig. 1, a lead frame 20, which is the member to be molded, is clamped by the upper die 10a and the lower die 10b.

Generally, in the molding method using the release film, the release film is set for each molding work. A method of setting the release film 30 of the present embodiment will be explained.

A sheet of the release film 30 is formed into a belt shape which has prescribed width for covering over the molding sections of the dies 10a and 10b. The release film 30 is sucked to fix on clamping faces, which are peripheral faces of the molding sections, of the dies. The release film 30 is formed not to interfere with guide pins 23, which locate the lead frame 20 at prescribed position on the die 10b.

Sucking air paths 32 are arranged in area covered with the release film 30, and they enclose edges of the cavities. When air is sucked through the sucking air paths 32, the release film 30 is sucked to fix on the clamping faces. Sucking force to fix the release film 30 is made greater when diameter of opening sections of the sucking air paths 32 is greater. The release film 30 is softened by the heat of the molding dies. Thus, the release film 30 is caught by sharp edges of the sucking air paths 32 when the release film 30 is sucked by the paths 32, so that the release film 30 is not drawn toward the cavities even if the release film 30 is sucked in the cavities.

As shown in Fig. 1, the sucking air paths 32 are communicated with air paths 34, which are formed in the plates 24a and 24b. The air paths 34 are communicated with an external air sucking mechanism A. The release film 30 is sucked to fix by air suction of the air sucking mechanism A.

The release film 30 is fixed along inner faces of the molding sections, e.g., the cavities, by the air suction. This sucking fixation is executed by sucking air through edges of the bottoms of the cavities. There are small gaps between the cavity pieces 22a and 22a and the through-holes of the dies in which the pieces 22a and 22b have been inserted. The gaps are cavity air paths 36 for drawing the release film 30 by the air suction. As shown in Fig. 1, the cavity air paths 36 communicated with air paths 38, which are formed in the plates 24a and 24b. The air paths 38 are communicated with an external air sucking mechanism B. Note that, width of one ends of the cavity air paths 36, which are opened along the edges of the bottoms of the cavities, are made narrower so as to suck the release film 30 effectively.

As shown in Fig. 2, the one ends of the cavity air paths 38 are opened to enclose the bottom of the cavities. The width of the one ends of the cavity air paths 38 is designed that the release film 30 is not drawn into the paths 38 when the release film 30 is drawn by the air suction, and that the release film 30 is not pushed into the paths 38 by resin pressure when the resin melt is filled into the cavities.

After the release film 30 is fixed on the clamping faces of the molding dies by the suction through the sucking air paths 32, the release film 30 is drawn through the cavity air paths 36. Then, the release film 30, which has been clamped by the clamping faces, is tightly fitted on the inner faces of the cavities. The release film 30 is made from a material, which is capable of extending by the air suction through the cavity air paths 36 and deforming along the inner shape of the cavities to fit on the inner faces thereof.

A fixing mechanism for fixing the release film 30 on the dies comprises the sucking air paths 32, the cavity air paths 36, and the external air sucking mechanisms A and B.

Air vents 59 are shown in Fig. 2. The air vents 59 are connected with corners of the cavities via sub-air vents 59a. The air vents 59 are extended until end faces

of the molding die. Since the lead frames 20 are clamped together with the release film 30, they do not directly contact the molding dies. But air ventilation can be executed via the sub-air vents 59a and the air vents 59 in spite of existing the release film 30. The air vents 59 are provided between adjacent cavities, and they act as means for accommodating the lead frames 20, so that the lead frames 20 can be securely clamped in the vicinity of the cavities.

In the present embodiment, since the inner faces of the cavities are covered with the release film 30, the resin does not directly contact faces of the molding sections. Further, wrapped resin 42 is supplied into the pot 12 so as to prevent the resin from directly contacting inner faces of resin paths, which connect the cull piece 26, the pot 12 and the cavities 21.

Fig. 3 shows a state of setting the wrapped resin 42 in the pot 12. The resin 40 is tightly wrapped between a lower wrapping film 44, which has a pocket section 44a in which the resin 40 is accommodated, and an upper wrapping film 46. The lower wrapping film 44 and the upper wrapping film 46 are mutually adhered. Epoxy resin and phenolic resin, for example, can be used as the thermosetting resin 40. The wrapped resin 42 is preferably formed by extruding a resin material so as to prevent air mixture.

Planar arrangement of the pot 12 and the wrapped resin 42 is shown in Fig. 2. In the present embodiment, the narrow rectangular pot 12 is arranged between the lead frames 20, which are located in parallel. Resin paths and gates 10c are extended from the pot 12 to each molding sections. The resin 40 in the wrapped resin 42 is formed into a thin stick shape to correspond to an inner shape of the pot 12. Heat exchanging efficiency of the stick resin 40 is greater than that of conventional resin formed into a columnar shape. The resin which has a sectional shape of an oblong shape has greater heat efficiency than the resin which has a sectional shape of a regular square shape. An end section of a plunger in the pot 12 is formed thin to correspond to the inner shape of the pot 12.

The wrapped resin 42, which is generally used, is shown in Fig. 4. Overlapped sections of the lower film 44 and the upper film 46 are tightly heat-sealed. The sealed sections are peeled off from the pot 12 by resin pressure for sending.

The lower film 44 and the upper film 46 have extended sections 48, which are extended from side edges of the films 44 and 46, so as not to stick the resin in the resin paths. To prevent the resin from sticking on the dies, the extended sections 48 are extended to overlap the release film 30, which is sucked to fix to the dies 10a and 10b.

When the extended sections 48 is extended to coincide with an end of the gates 10c, the lead frames 20 can be molded without sticking the resin on the lead frames 20. In the case of sticking no resin on the lead frames 20, a step of breaking gates is not required, so

that deformation of the molded lead frames can be prevented.

To precisely coincide the extended sections 48 with the ends of the gates 10c, pilot pins 50a and 50b are inserted through pilot holes, which have been bored in the wrapping films. The pilot pin 50a is located near one end of the wrapped resin 42; the pilot pins 50b are located at base sections of the extended section 48.

The wrapped resin 42 may be set with a jig for setting into the pot 12 instead of the pilot pins 50a and 50b. As shown in Fig. 5, the wrapped resin 42 is sucked by a sucking pad 52 of the setting jig. The wrapped resin 42 is precisely positioned by a positioning pin 53. There is bored a positioning hole 50c into which the positioning pin 53 is inserted in the molding die. With this structure, the extended sections 48 can be coincided with the gates 10c when the wrapped resin 42 is set in the pot 12 with the setting jig. In the case of boring the pilot hole 50c in the molding die, setting and positioning the lead frames 20 are easier than the case of providing the pilot pins 50a and 50b.

To prevent the edges of the wrapping film from turning over and to securely hold the same when the wrapped resin 42 is set into the pot 12, there is bored sucking holes 54 in the lower die 10b. As shown in Fig. 2, the sucking holes 54 is bored along the edges of the wrapping film with prescribed intervals. The sucking holes 54 is opened in bottom faces of female cone sections 54a respectively (see Fig. 6). The female cone sections 54a make sucking area to securely suck the films. The female cone sections 54a are arranged parallel to the edges of the wrapping films. The sucking holes 54 are also communicated with the air paths in the plate 24b and the eternal air sucking mechanism.

Note that, another method in which the resin is slightly stuck on the lead frames 20 and the wrapped resin 42 is not so severely positioned may be actually employed. In Fig. 7, the resin is stuck on a part 20b of the lead frame 20. Length of sticking the resin is designed that the resin solidified on the lead frame 20 is not easily peeled off from the lead frame 20 while a handling step after molding.

As shown in Fig. 3, the resin melt is filled in the cavity 21 via a gap between the lower wrapping film 44 and the upper wrapping film 46. In the present embodiment, the gates 10c are provided in the lower die 10b, so the wrapping films 44 and 46 are provided between the lead frames 20 and the release film 30, which has been fixed on the lower die 10b.

In the right side of Fig. 3, the resin is filled in the cavity 21 via the gate 10c. The resin, which is pressurized and sent from the pot 12, enlarges the gap between the lower film 44 and the upper film 46 in the gate 10c, then flows into the cavity 21. The resin sent from the pot 12 is prevented to contact the cull piece 26 by the upper wrapping film 46.

The resin 40 is pushed out from the pot 12 by the plunger 13 together with the wrapping film, which has

tightly wrapped the resin 40, so that no resin is stuck on an inner face of the pot 12 and the plunger 13.

In the case of setting the wrapped resin 42 into the pot 12, no resin leak occurs therein, so that the plunger 13 need not to be precisely fitted in the pot 12. Thus, the pot 12 may be formed by boring a mere rectangular hole or circular hole in a die material. Further, since no bushing is required in the pot 12, the resin paths can be arranged close to the pot 12, so that the die can be small in size. If the pot 12 and the plunger 13 are made of materials having high heat conductivity, e.g., copper, aluminum, heat exchange between the resin and them can be accelerated, so that the resin 40 can be melt in a short time.

The wrapped resin 42 has the extended sections 48, which are extended from the films 44 and 46 to coincide with the gates 10c. Enlarged view of the extended section 48 is shown in Fig. 8. The extended section 48 is coincided with a connecting section of the cavity 21 and the gate 10c.

On the other hand, the wrapping films 44 and 48 shown in Fig. 9 have no extended sections. Side edges of the films 44 and 46 are linearly formed and located in the vicinity of the cavity 21. The gate 10c passes the side edge of the film 44 and reaches the cavity 21. The lead frame 20 has a vacant gate window 20a, to which the gate 10c corresponds; the molding die has a dam block 20c whose shape is corresponded to the gate window 20c and whose thickness is equal to that of the lead frame 20. Since the release film 30 covers over the dam block 20c and the cavity 21 while molding, the resin is filled into the cavity 21 without contacting the lead frame 20 even if the wrapping films 44 and 46 do not reach the connected section of the gate 10c and the cavity 21. The resin flows in the resin path, which is covered with the release film 30.

As described above, the resin can be prevented to stick on the lead frame 20 without the extended sections 48. In the case of employing the extended sections 48, the wrapped resin 42 for exclusive use must be prepared; in the case of employing no extended sections 48, the wrapped resin 42 for wide use can be used.

In the case of the lead frame 20 having the gate window 20a (see Fig. 9), the resin can be filled via the gates 10c, which are formed in the upper die 10a and the lower die 10b, as shown in Fig. 10. By providing the gates 10c in the dies 10a and 10b to correspond to the gate window 20a, the resin flow is branched by the gate window 20a, so that the resin is filled into the cavity from the upper gate 10c and the lower gate 10c.

As described above, in the present embodiment, the molding sections of the molding dies are covered with the release film 30, and the wrapped resin 42 is supplied. Thus, no resin directly contacts the molding dies while molding. The release film 30 will be newly drawn in the longitudinal direction for each molding work, so that new release film 30 can be set on the dies for each cycle.

In the present embodiment, the molding sections have the cavity pieces 22a and 22b so as to form the cavity air paths 36 for fixing the release film 30 along the inner shapes of the molding sections. By selecting the shapes and the sizes of the cavity pieces 22a and 22b, the shapes and the sizes of the cavity air paths 36 can be optionally formed.

Plan views and sectional views of the cavities having the cavity pieces 22 of other examples are shown in Figs. 11A - 15B.

In Figs. 11A and 11B, the shape of the opening section of the cavity air path 36 is the same as the above described one. The cavity air path 36 is opened along connected sections of the inner bottom face of the cavity and inner side faces thereof. The cavity air path 36 encloses the inner bottom face of the cavity.

In Figs. 12A and 12B, the cavity air paths 36 is opened only in the inner bottom face of the cavity; no cavity air paths 36 is opened in any inner side faces thereof. The cavity air path 36 is partially opened at four positions in the bottom face. In this case, cut sections are formed on outer side faces of the cavity piece 22.

In Figs. 13A and 13B, the cavity air paths 36 is opened in the inner side faces of the cavity. In this case, outer side faces of the cavity piece 22 are formed flat; the cut sections are partially formed on inner side faces of the through-hole of the molding die.

In Figs. 14A and 14B, the cavity air paths 36 is opened both in the inner bottom face and the inner side faces of the cavity. In this case, the cut sections are partially formed both on the outer side faces of the cavity piece 22 and on the inner side faces of the through-hole of the molding die.

In Figs. 15A and 15B, the cavity air paths 36 is diagonally opened like slits from corners of the inner bottom face of the cavity, which are not connected with the gate 10c. Further, the cavity air path 36 is opened like a circular hole at position 36a, which is slightly separated away from a corner of the inner bottom face of the cavity to which the gate 10c is connected toward the center of the bottom face.

As shown in Figs. 12A, 12B, 13A, 13B, 15A and 15B, the opening sections of the cavity air paths 36 are arranged to separate away from the corner of each inner bottom face of the cavity to which the gate 10c is connected. Considering the resin flow in the cavities, the opening sections of the cavity air paths 36 are arranged as described above so as to properly fill the resin in the cavities.

In Figs. 16A and 16B, the cavity air path 36 is also provided to separate away from the gate 10c. Note that, Fig. 16B is a sectional view taken along the line C-C. When the release film 30 is sucked by the air path 36, the release film 30 is slightly raised like a shallow slope in the vicinity of an inner end of the gate 10c. The conventional molding machines have a problem of air mixture at a position immediately below the inner end of the gate 10c. But, by forming the shallow slope of the release film 30, a steep slope, which causes the air mix-

ture, is removed at the position immediately below the inner end of the gate 10c, so that the air mixture can be prevented while molding. By preventing the air mixture, high quality molded products, which have no voids in the molded sections, can be produced.

In Figs. 17A and 17B, another example of the cavity air path 36 whose opening sections are also separated away from the gate 10c is shown. The opening sections of the cavity air path 36 are opened in the center area of the bottom face thereof. The release film 30 is not sucked in the vicinity of the edges of the bottom face. By sucking the release film 30 only in the center area of the cavity, the release film 30 are raised in the vicinity of the edges of the cavity, so that the resin melt is able to smoothly flow in the center area thereof, and air mixture in the center area can be prevented. Note that, air vents 55 are formed in the die.

In the case of providing the opening sections of the air path 36 in the center area of the cavity, a state of filling the resin is shown in Fig. 18A; in the conventional molding machine, a state of filling the resin is shown in Fig. 18B. When the lead frames are molded, a semiconductor chip is located at the center of the cavity, so the resin flow in the center area thereof is restricted by the chip in the conventional molding machine. At the beginning the resin flows in the vicinity of the chip, so that air is shut in the center area (see Fig. 18B). On the other hand, in the example shown in Fig. 18A, firstly the resin fills the center area, then the resin fills around the chip. Thus, air is pushed outward, so that high quality molding can be executed.

Other manners of assembling the cavity pieces 22 in the base sections of the molding dies are shown in Figs. 19A, 19B and 20. In Fig. 19A, area of an upper end face of the cavity piece 22 is broader than area of a cavity hole 11a. The cavity piece 22 is inserted in the through-hole 11b for assembling the cavity piece 22. There is formed a gap for sucking air from the bottom of the cavity between the cavity piece 22 and the through-hole 11b. The cavity hole 11a and the through-hole 11b are bored in the base section of the molding die 10b.

In Fig. 19B, the cavity hole 11a and the through-hole 11b are integrated to form into one hole. The block shaped cavity piece 22 is inserted in the through-hole 11b. As well as the example of Fig. 19A, no draft angle is formed in the side faces of the cavity, so that it is easier to make the molding dies. Of course, the draft angle may be formed in the side faces of the cavity. In this example, thickness of molded products can be changed by changing thickness of the cavity piece 22.

In Fig. 20, the base section of the molding die has two parts: a first part for forming the cavity; and a second part for inserting the cavity piece 22. The base section 10d or the first part has the depth equal to the depth of the cavity. The cavity piece 22 is inserted in the base section 10e or the second part. There is bored the cavity hole 11a for forming the cavity in the base section 10d; there is bored the through-hole 11b for inserting the cavity piece 22 in the base section 10e. With this

structure, the base sections 10d and 10e can be made easily. Further, by employing the first part 10d and the second part 10e, the cavity can be formed without the cavity piece 22.

In the present embodiment, the cavity and the cavity air path 36 are formed by assembling the cavity piece 22 in the base section of the die. But they can be formed without the cavity piece 22. This example is shown in Figs. 21A and 21B. Fig. 21A is a plan view in which the opening sections of the cavity air path 36 are diagonally opened toward the center of the cavity like slits. And a plurality of circular opening sections of the cavity air path 36 are arranged in the bottom face of the cavity along the edges thereof. Fig. 21B is a sectional view taken along the line D-D. In this example too, no opening section of the cavity air path 36 are provided in the vicinity of the corner of the cavity to which the inner end of the gate 10c is connected; the opening sections are separated away from the corner, so that the resin can be properly filled in the cavity as well as the example shown in Figs. 15A and 15B.

Sucking and fixing the release film 30 is shown in Fig. 22. The graph P shows action of the air sucking mechanism A for sucking air to fix the release film 30 on the faces of the dies; the graph Q shows action of the air sucking mechanism B for sucking air to fix the release film 30 on the inner faces of the cavity. Firstly, the release film 30 is sucked and fixed on the faces of the die by the air sucking mechanism A, slightly after then the air sucking mechanism B sucks the release film 30 to fix in the cavity. After the release film 30 is completely fixed on the die, the resin melt is started to fill the cavity. A point R indicates completing to fill the resin; a point S indicates completing solidification of the resin. The air suction is stopped slightly before the point S.

After the molding, the molding dies are opened, then the molded products are ejected from the dies together with the release film 30. If the air sucking mechanisms A and B blow air, the products can be ejected easier. A part T in Fig. 21 indicates the action of blowing air.

By employing the release film 30, the resin molding machine of the present embodiment has following effects. Since no ejector pins are required, the structure of the molding dies can be simpler, and they can be made easier. Materials which are not hard can be employed for making the molding dies. Since flow resistance of the resin can be reduced, the resin paths can be thinner. Since polishing the resin paths is not required, it is easier to make the molding dies. Since the molding dies can be made by assembling parts members in the base section, changing degree of surface roughness and marking can be easily executed by only changing the parts members. Heat treatment, precise surface treatment and plating can be omitted for making the molding dies. Since the resin is not stuck on the molding dies, removing flashes and cleaning are not required. Further, no chemical agents for easily peeling the resin off from the dies are required to mix with the resin.

In the above described examples, the release film 30 is fixed on the molding sections of the molding dies by sucking air through the cavity air paths 36. Further, the cavities may be made of a porous metal instead of forming the cavity air paths 36. In this case, air is sucked through the porous metal sections to fix the release film 30. Even if the molding sections are made of the porous material, the molding sections are covered with the release film 30, so that no problem occurs.

The release film 30 is capable of easily peeling off from the molding dies and the molded products. If the release film 30 is made of porous film having fine holes with diameter of about 20 μm or film in which fine holes with diameter of about 20 μm are bored by laser, etc., the molding method has following effects. By using the porous release film, air in the cavities and gas generated from the resin can be discharged through the fine holes without passing the resin. Air ventilation can be executed more effectively through the fine holes than through the air vents, so that high quality molding can be executed.

A state of leaking the resin from the fine holes 30a of the release film 30 is shown in Fig. 23. While the molding, not oily air and but also the resin melt are discharged via the fine holes 30a. To prevent the leakage, a treatment for easily peeling off, e.g., applying fluoric resin, may be treated on the faces of the molding dies. The resin leaked out from the fine holes 30a solidify on the both faces of the release film 30, so that the resin solidified can be peeled from the faces of the dies, which have been treated. The resin solidified is discharged from the dies together with the release film 30, so that the dies can be maintained clean. The fluoric resin layer 56 is shown in Fig. 23. Note that, the surface treatment of the molding dies, e.g., forming the fluoric resin layer 56, may be treated in the case of using the release film 30 having no fine holes so as to deal with the resin leakage.

In the present embodiment, by using the release film 30, the materials having high heat conductivity, e.g., copper, aluminum, can be used for the molding dies, so that the heat exchange between the resin and the dies can be accelerated. Thus, resin can be solidified in a shorter time, and the molding cycle time can be shortened. Examples of the high heat conductivity materials and their heat conductivity are as follows: Ni-Cr alloy (k) = $37\text{W} \cdot \text{m}^{-1} \cdot \text{K}^{-1}$ (180°C); 18-8 stainless steel (k) = $18\text{W} \cdot \text{m}^{-1} \cdot \text{K}^{-1}$ (180°C); carbon steel (k) = $47\text{W} \cdot \text{m}^{-1} \cdot \text{K}^{-1}$ (180°C); Fe (k) = $65\text{W} \cdot \text{m}^{-1} \cdot \text{K}^{-1}$ (180°C); Cu (k) = $385\text{W} \cdot \text{m}^{-1} \cdot \text{K}^{-1}$ (180°C), etc..

The molding dies have the heaters 23 and they can be made of many kinds of materials, so that it is easier for the molding machine of the present embodiment to precisely control the temperature of the dies than the conventional machines. Further, solidification time of the resin, filling-ability of the resin into the cavities, and solidification process of the resin therein can be improved.

Namely, for example, in the case that the solidification process in the upper die 10a and the lower die 10b are different, the filling-ability of the resin into the cavities can be improved. In Fig. 24, since a semiconductor chip is set in the cavity 14 of the lower die 10b, the resin solidification time in the lower die 10b is designed longer than that in the upper die 10a so as to easily fill the resin in the lower die 10b. Thus, the temperature of the lower die 10b is lower than that of the upper die 10a. The heat conductivity of members 66 are different each other.

The above described heat control is effective in the cases of: molding thin products wherein the filling-ability of the resin into the cavities is an important factor; products whose thickness is partly different; products having heat sinks. Not only by controlling the temperature of the heaters 23 but also by employing different materials, whose heat conductivity are mutually different, for the upper die 10a and the lower die 10b, the temperature of the upper die 10a and the lower die 10b can be different.

When the gates of the molding dies are made of a material whose heat conductivity is lower than that of the cavities, the filling-ability of the resin into the cavities can be improved. By braking the solidification of the resin in the gates, the resin can be filled into the cavities easier. If the gates are heat-insulated from the other parts of the molding dies, the temperature of the gates can be lower than that of the other parts, so that the filling-ability of the resin into the cavities can be improved. Further, if the resin paths for introducing the resin into the cavities are made of materials whose heat conductivity is different from other parts of the dies, flowability of the resin in the resin paths is also improved.

In the case of employing the materials having high heat conductivity for center parts of the cavities, the resin solidification in the center area of the cavities can be accelerated, so that curvature of molded parts of products while and after solidification can be prevented. The materials having different heat conductivity may be arranged other portions of the cavities. And a plurality of the materials may be arranged in one cavity. Furthermore, the temperature of the molding die can be partially different by controlling the heaters.

In the present embodiment, the gates 10c are provided in the lower die 10b. They may be provided in the upper die 10a as shown in Fig. 25. By providing the gates 10c in the upper die 10a, the wrapping film 44 of the wrapped resin 42 is mounted on the lead frame 20. Other structures are the same as the example shown in Fig. 3.

[Structure of The Release Film]

In the above described examples, the release film 30 is a mere sheet of film without any additional members. Another release film for the molding machines is shown in Fig. 26. The release film 30 has a transferring layer 60 on the film surface. The transferring layer 60 can be transferred and fixed onto a surface of the solid-

ified resin. An aluminum heat sink, thin metal film, etc. can be employed as the transferring layer members. The transferring layer 60 may be formed so as to transfer letters, patterns, etc. onto the surface of the molded products. The transferring layer 60 has been previously adhered on a film material of the release film 30 with an adhesive. The adhesive is capable of resisting the molding temperature of the molding dies, and the adhesive force must be greater than flow-force of the resin filled into the cavities so as not to deform the transferring layer 60 and not to move the position of the layer 60.

A state of sucking the release film 30 to fix on the molding dies and clamping the lead frame 20 is shown in Fig. 27. The transferring layers 60 are adhered on a cavity side of each release film 30 with the adhesive 60a. In Fig. 27, the both release films 30 have the transferring layers 60. In the upper release film 30, the transferring layer 60 is provided to correspond to semiconductor chips 70; in the lower release film 30, the transferring layer 60 is provided to cover over the bottom faces of the cavities. The transferring layers 60 are transferred and fixed onto the molded packages with adhesive force of the thermosetting resin solidifying.

By providing the transferring layer 60 on the release film 30, the heat sink, the metal film, the patterns, etc. can be simultaneously provided to the molded package while the molding. In the conventional molding machine, the heat sink, for example, is molded together with a semiconductor chip, to expose from the resin package. By this conventional method, the resin invades into a thin space between the heat sink and the face of the molding die, so that thin flash is formed therein; by transferring the heat sink as the transferring layer 60, forming the thin flash can be prevented.

Optional patterns can be employed as the transferring layer 60. The patterns in the transferring layer 60 must be formed considering positions of the members to be molded, so that the transferring layer 60 must be precisely positioned on the molding dies. To precisely position the transferring layers 60, feeding holes 30b may be bored in the side edge sections of the release film 30 as shown in Fig. 26. Pitch of the feeding holes 30b is equal to that of the cavities. The feeding holes 30b are formed in one or both side edge sections of the release film 30.

When the heat sink is fixed by the transferring method with the release film having the fine holes, forming voids in the vicinity of the heat sink can be effectively prevented because air is discharged via the fine holes even if air is concentrated in the vicinity of the heat sink.

A condition on the surface of the molding dies can be copied on the surface of the molded products. For example, in the case of forming the surface of the products into a rough surface, the surface of the molding die is formed into a rough surface; in the case of forming the surface of the products into a smooth surface, the surface of the molding die is formed into a smooth surface. Further, in the case of forming a mark on the surface of

the products, the mark is formed on the surface of the molding die.

In Fig. 28, a BGA substrate 60 is employed as the transferring layer. The release film 30 on which the BGA substrate 60 has been adhered is clamped by the upper die 10a and the lower die 10b to mold. With this structure, a semiconductor device in which one side of the BGA substrate 60 is molded together with a semiconductor chip can be manufactured. The BGA substrate 60 may be left from the release film 30 while molding; the BGA substrate 60 may be discharged together with the release film 30 and left from the release film 30 in the next manufacturing step. This method has an advantage of conveying the BGA substrates 60 together with the release film 30.

[Adjusting A Gap between The Clamping Faces]

Stopper blocks 80 are shown in Fig. 1. The stopper blocks 80 are capable of adjusting a gap between the clamping faces of the molding dies 10a and 10b when the dies 10a and 10b are in a state of clamping. The stopper blocks 80 are fixed on the upper die 10a or the lower die 10b. They are capable of contacting the clamping face of the opposite die to adjust the gap between the clamping faces of the dies 10a and 10b. The stopper blocks 80 are exchangeable, so that said gap can be adjusted.

Since the release film 30 has enough softness, the stopper blocks 80 do not damage the release film 30 despite the molding sections and the clamping faces of the molding dies are covered with the release film 30 when they clamp the lead frames 20. And degree of compressing the release film 30 in the state of clamping the lead frames 20 can be adjusted, so that proper molding can be executed.

By adjusting clamping force of the dies by the stopper blocks 80, disuse projections, etc. of the lead frame 20, which are formed in the process of making the lead frame 20, can be absorbed. If the thickness of the release film 30 can be compressed about 25 %, the disuse sections of the lead frame 20 can be absorbed in the film 30, so that the lead frame 20 can be molded without forming thin flashes. The clamping force of the molding dies can be reduced to 1/5 - 1/4 of the conventional ones.

By using the release film 30, distribution of the thickness of the members to be molded, e.g., lead frames, can be absorbed, so that they can be molded properly.

By adjusting the gap between the dies 10a and 10b, dam-barless lead frames can be molded. Since the release film 30 can be compressed to about 20 % of the initial thickness, the compressed sections act as dam-bars. A state of molding the dam-barless lead frame 20 is shown in Fig. 29. Outer leads are shown with a symbol 20a.

By using the compressible release film 30, the gap between the dies 10a and 10b can be easily adjusted by

a die-clamping mechanism, which is driven by a servo motor, etc., without the stopper blocks 80. For example, firstly clamping movement of the die is once stopped about 0.02 mm before a regular clamping position: first compression, then the resin is filled into the cavities. The die is moved again until reaching the regular clamping position while the resin is solidifying: second compression. With this method, shrinkage of the resin while solidifying can be covered by the second compression, so that deformation of the molded portion, e.g., curvature, can be prevented.

[The Structures of The Pot And The Plunger]

As shown in Fig. 1, the sectional shape of the plunger 13 is made thinner toward a front end. By forming the plunger 13 into said shape, piling the wrapping film 44 like bellows can be prevented even if the plunger 13 lifts up the resin, so that the resin paths cannot be closed by the film 44.

The structure of the pot and the plunger shown in Figs. 30 and 31 is effective to prevent the resin paths from closing.

An upper part of the pot 12 is formed like a funnel with inclined faces 12a. There is provided an air trap 90 in the cull section of the upper die 10a, which faces the pot 12. The plunger 13 has a tapered section 13a made thinner toward an upper end.

The air trap 90 is capable of trapping air, which is generated from the resin melt in the pot 12. The air trap 90 is faced the pot 12 and formed into a groove.

The wrapped resin 42 is supplied into the pot 12. A gap between the outer faces of the plunger 13 and the inner faces of the pot 12 is designed to prevent the wrapping film 44 from invading thereinto.

In Fig. 30, the left side of the center line shows a state of before filling the resin into the cavities; the right side of the center line shows a state of beginning to lift the plunger 13 to fill the resin.

Air in the resin melt climbs upward by buoyant force, then trapped in the air trap 90, so that forming air voids in the cavities can be prevented. Resin pressure applied by the plunger 13, so that the wrapping films 44 and 46 are extended along the inner faces of the gates 10c and the inclined faces 12a of the pot 12, and the resin is filled into the cavities.

In Fig. 31, the left side of the center line shows a state of slightly before completely filling the resin into the cavities; the right side of the center line shows a state of completely filling the resin therein. With the lifting of the plunger 13, the wrapping film 44 is gradually loosened, and the loosened section of the film 44 piles on the outer faces of the plunger 13. By forming the tapered section 13a of the plunger 13 and the inclined faces 12a of the pot 12, an accommodating space for accommodating the loosened section of the wrapping film 44 is formed, so that closing the resin paths by the loosened section of the film 44 can be prevented.

Since the wrapping film 44 does not close the resin paths, the plunger 13 is capable of completely filling the cavities with prescribed pressure.

The resin solidified in the pot 12 can be easily removed by merely pushing the resin upward by the plunger 13 because the wrapping film 44 is not caught in the pot 12 and the inclined faces 12a of the pot 12 releases the solidified resin in the pot 12.

In the case that the upper part of the plunger 13 is formed thinner toward the upper end, lifting the wrapping film 44 upward can be prevented but pressurizing the resin cannot be effectively executed. On the other hand, in the case that the upper end face of the plunger 13 is formed flat, pressurizing the resin can be effectively executed but lifting the wrapping film 44 upward cannot be prevented. Considering the both conditions, proper angle of the tapered faces 13a of the plunger 13 with respect to the vertical line is about 45°. Further considering the film piling space and the hardness of the film, proper angle thereof may be 30° - 60°. If angle of the inclined faces 12a of the pot 12 with respect to the vertical line is greater, amount of the resin supplied into must be larger, so the proper angle will be small: 1° - 15°.

In examples shown in Figs. 32 and 33, the pots 12 has no inclined faces 12a. In Fig. 32, the left side of the center line shows a state of before beginning to fill the resin; the right side of the center line shows a state of after beginning to fill the resin. In Fig. 33, the left side of the center line shows a state of slightly before completing to fill the resin; the right side of the center line shows a state of completing to fill the resin.

By forming the tapered section 13a of the plunger 13, the invasion of the wrapping film 44 into the pot 12 can be prevented while sending the resin by the plunger 13. But, without the inclined faces 12a, the wrapping film 44 is apt to tightly pile on the outer side of the plunger 13, so that it will be difficult to discharge the solidified resin from the pot 12.

Note that, in the case of using the flat-end plunger 13 with no tapered section 13a and forming the inclined faces 12a in the pot 12, lifting the wrapping film 44 upward can be properly prevented.

Another structure of the pot and the plunger is shown in Fig. 34. In this example, the tapered faces 13a are formed on both sides of the plunger 13. There are formed step sections 13b in base sections of the tapered faces 13a. The upper end face of the plunger 13 is formed into a flat face. There are formed the inclined faces 12a like a funnel in the pot 12. And there are formed step sections 12b in base sections of the inclined faces 12a. Length DA between the edge of the upper end of the plunger 13 and the base section of the tapered section 13a is designed about twice the size of thickness of the wrapping film 44; the gap between the outer faces of the plunger 13 and the inner faces of the pot 12 is 1/2 of the thickness of the wrapping film 44. By forming the step section 13b, the space for accommodating the loosened sections of the wrapping film 44 can

be formed, and invading the wrapping film 44 into a portion below the step section 13b can be prevented. This structure is effective for the case of using the thinner wrapping film 44 whose thickness is 50 μm or less.

(Second Embodiment)

A one-side resin molding machine with the release film will be explained as Second Embodiment.

In Fig. 35, substrates 5 are held by the upper die 10a; the cavities 11 are formed in the lower die 10b. The left side of the center line shows a state of clamping the substrate 5; the right side of the center line shows a state of filling the resin in the cavity 11.

The release film 40 covers over the cavities 11 of the lower die 10b. The cavity pieces 22 are attached in the lower die 10b. The release film 30 is sucked to fix on the lower die 10b by the manner as will as the First Embodiment so its explanation is omitted.

The substrates 5 are held in the upper die 10a by means for sucking the substrates 5. As shown in Fig. 36, air sucking holes 124a and 124b are formed in the upper die 10a, and they are communicated with an air path 125 in the plate 24a. The air path 125 is connected to an external air sucking mechanism. Pocket sections 126 are formed in the parting face of the upper die 10a, and their depth is equal to the thickness of the substrate 5. The air sucking holes 124a and 124b are opened in bottom faces of the pocket sections 126. Pilot pins 128 are capable of positioning the substrates 5 in the pocket sections 126. Note that, in Fig. 36, the left side of the center line shows a state of not holding the substrate 5; the right side of the center line shows a state of holding the substrate 5.

Planar arrangement of the air sucking holes 124a and 124b, the pilot pins 128, etc. is shown in Fig. 37. In Fig. 37, the left side of the center line shows a state of not holding the substrate 5; the right side of the center line shows a state of holding the substrate 5. A plurality of the air sucking holes 124a are opened in the bottom faces of the pocket sections 126; each air sucking hole 124b is opened like a rectangular slit along the edge of the bottom face of each pocket section 126. Two pilot pins 128 are provided to each couple of diagonal corners of the pocket section 126 so as to contact side faces of two corners of the substrate 5 to position.

The pilot pins 128 are capable of projecting from and retracting into the upper die 10a by an air driving mechanism. Air paths 129a and 129b are connected to an external air mechanism to drive the pilot pins 128. The pilot pins 128 are driven by charging and discharging compressed air via the air paths 129a and 129b.

When the substrates 5 are held in the pocket sections 126, the pilot pins 128 are projected from the parting face of the upper die 10b so as to contact the side faces of the substrate 5 to position.

The step of setting the substrate 5 in the upper die 10a to the step of setting the release film 30 on the lower die 10b are shown in Figs. 38 - 40. In the present

embodiment, the substrate 5, which has formed into a piece of board, is set in a conveying jig 130, and the substrate 5 is sent into the molding machine by the jig 130, then the substrate 5 is set in the molding machine.

An opening state of the molding dies 10a and 10b is shown in Fig. 38. The jig 130 holding the substrate 5 is sent to a position under the parting face of the upper die 10a. And the belt like release film 30 is fed on the lower die 10b. The jig 130 has a setting section in which the substrate 5 is correctly set, an air path for blowing the substrate 5 upward by air pressure, and a pilot hole 130c into which the pilot pin 128, which has been projected, is capable of inserting.

Next, the jig 130 is lifted to move close to the upper die 10a as shown in Fig. 39. Then the pilot pin 128 is projected from the parting face of the upper die 10a and contacts the side face of the substrate 5 to position the same with respect to the upper die 10a.

On the other hand, the release film 30 is sucked by the sucking air path 32, which is formed under the clamping face of the lower die 10b. By this sucking, the side edge of the release film 30 is fixed on the lower die 10b.

Successively, the substrate 5 is held and positioned in the pocket section 126 of the upper die 10a by sucking air through the air sucking holes 124a and 124b. Note that, by blowing the compressed air from the air path 130b of the jig 130, the substrate 5 can be easily held by the upper die 10a. Fig. 40 shows a state of moving the jig 130 outside of the dies after the substrate 5 is held by the upper die 10a.

On the other hand, the release film 30 is sucked and fixed in the cavity along the inner faces of the cavity by sucking air through cavity air paths 36.

After the substrate 5 and the release film 30 are held in the upper die 10a and the lower die 10b, the resin is supplied into the pot 12. Then the dies are closed, and the resin is filled into the cavity.

The action of the pilot pin 128 while closing the dies will be explained with reference to Figs. 41 and 42. In Fig. 41, a pilot hole 132 into which the pilot pin 128 inserts is bored in the lower die 10b. When the molding dies 10a and 10b are closed in a state of projecting the pilot pin 128 from the clamping face of the upper die 10a, the pilot pin 128 breaks the release film 30 and goes into the lower die 10b.

In Fig. 42, there is no pilot hole 132 in the lower die 10b. A lower end of the pilot pin 128 contacts the release film 30 on the clamping face of the lower die 10b. When the molding dies 10a and 10b are closed, the pilot pin 128 is retracted into the upper die 10a.

In the manner shown in Fig. 41, the substrate 5 can be more securely and precisely positioned than the manner shown in Fig. 42.

After clamping the substrate 5, the wrapped resin is filled in the cavity to mold. The manner for molding with the wrapped resin is also the same as that of the First Embodiment.

With above described manner, one side of the substrate 5 can be molded with the release film 30. Note that, in the present embodiment, the substrate 5 is held by the upper die 10a, but the substrate 5 may be held by the lower die 10b, and the gate may be provided in the upper die 10a.

Since the inner faces of the molding sections of the molding dies are covered with the release film 30, the release film 30 acts as the dam-bar of the lead frame when the substrate 5 is clamped by the dies 10a and 10b, so that the substrate 5 can be mold without any protecting treatment, e.g., solder resist. Namely, the release film 30 is compressed by the clamping force of the molding dies, which clamp the substrate 5 together with the release film 30, so that the compressed release film 30 closes gaps between wire patterns, which have been formed on the substrate 5. By this dam-bar function of the compressed release film 30, leakage of the resin from the gaps between the wire patterns can be prevented. When the release film 30 is used as the dam-bar, the clamping force of the molding dies 10a and 10b is defined on the basis of thickness of the wire patterns, distance between the wire patterns, elasticity of the release film 30, etc..

In the present embodiment, the substrate 5 can be molded without coating solder resist, the resin can be tightly adhered to the substrate 5. Since invading the solder resist into the cavities can be prevented, the quality and the reliability of the molded products can be raised. By clamping the substrate 5 together with the release film 30, the clamping force can be reduced to about 1/4 of the conventional manner, so that damaging the release film 30 and any trouble based on the damaging can be reduced. And by molding with the release film 30, the molded products can be easily ejected from the die together with the release film 30. Further, the release film 30 can be easily peeled off from the resin, so thin products can be molded properly.

(Third Embodiment)

Third Embodiment of the resin molding machine with the release film is shown in Fig. 43. It is for molding chip-size packages.

In the present embodiment, the release film 30 is sucked and fixed on the upper die 10a and the lower die 10b. The semiconductor chip 7 is clamped by the molding dies 10a and 10b to mold. The lower die 10b has a concave section 8 in which the chip 7 is set. Size of the concave section 8, in which the release film 30 is sucked, is about 0.5 mm larger than the chip 7. The clamping face of the upper die 10a is formed flat. The chip 7 is clamped by the dies 10a and 10b together with the release film 30.

A part to be molded is an exposed part, which is an edge section of wire patterns on the chip 7. When the chip-size package is molded with the resin, the chip 7 is clamped by the upper die 10a and the lower die 10b, simultaneously the chip 7 is pushed for centering in the

concave section 8 by a cam mechanism. The resin is filled into the concave section 8 in which the chip 7 has been correctly positioned via the gate 10c. By clamping the chip 7 together with the release film 30, invading the resin onto a rear face of the chip 7 and a face to which terminals, e.g., solder balls, are connected can be prevented, so that the quality and the reliability of the chip-size packages can be raised.

Claims

1. A resin molding machine, comprising:
 - molding dies (10a, 10b) having molding sections including cavities (21), said molding dies (10a, 10b) being capable of clamping a member (20) to be molded; and
 - a pot (12) for pressurizing resin melt to send the same to the cavities (21),
 - characterised by:
 - a fixing mechanism for fixing release film (30), which is capable of easily peeling off from said molding dies (10a, 10b) and resin for molding, on inner faces of the molding sections and clamping faces, which are peripheral faces of the molding sections, said fixing mechanism fixing said release film (30) by sucking air.
2. The resin molding machine according to Claim 1, further comprising an air sucking mechanism for sucking air, and
 - wherein said fixing mechanism comprises:
 - a sticking air path (32) whose one end is opened in the clamping end, and whose the other end is connected to said air sucking mechanism; and
 - a cavity air path (36) whose one end is opened in the molding section, and whose the other end is connected to said air sucking mechanism.
3. The resin molding machine according to Claim 2, wherein the cavities (21) are formed by fitting cavity pieces (22a, 22b) in attachment holes, which are formed in base sections of said molding dies (10a, 10b), and
 - wherein said cavity air path (36) is a gap between an inner face of the attachment hole and an outer side face of the cavity piece (22a, 22b).
4. The resin molding machine according to Claim 2, wherein the one end of said cavity air path (36) is opened in a peripheral of an inner bottom face of the cavity (21).
5. The resin molding machine according to Claim 3, wherein the one end of said cavity air path (36) is opened at a position separate away from one corner of the cavity (21) at which a gate (10c) is connected.
6. The resin molding machine according to
 - wherein said molding sections are made of a material whose heat conductivity is different from that of base sections of said molding dies (10a, 10b), and
 - wherein said molding sections are fitted in the base sections.
7. The resin molding machine according to Claim 3, wherein said cavity pieces (22a, 22b) are made of a material whose heat conductivity is different from that of the base sections of said molding dies (10a, 10b).
8. The resin molding machine according to Claim 6, wherein heat conductivity of an upper die (10a) of said molding dies is different from that of a lower die (10b) thereof.
9. The resin molding machine according to Claim 6, further comprising a heater (23) being provided in the molding section of one of said molding dies (10a, 10b).
10. The resin molding machine according to Claim 1, further comprising a stopper block (80) being provided to one of said molding dies (10a, 10b), said stopper block (80) defining a separation between said molding dies (10a, 10b) when said molding dies (10a, 10b) clamp the member (20) to be molded.
11. A resin molding machine, comprising:
 - molding dies (10a, 10b) having molding sections including cavities (21), said molding dies (10a, 10b) being capable of clamping a member (5) to be molded; and
 - a pot (12) for pressurizing resin melt to send the same to the cavities (21),
 - characterised by:
 - sucking means for sucking the member (5) to be molded to fix, said sucking means being provided in one of said molding dies (10a, 10b); and
 - a fixing mechanism for fixing release film (30), which is capable of easily peeling off from said molding dies (10a, 10b) and resin for molding, on inner faces of the molding sections and clamping faces, which are peripheral faces of the molding sections, said fixing mechanism being provided in one of said molding dies (10a, 10b) which is the opposite die to the die having said sucking means, said fixing mechanism fixing said release film (30) by sucking air.
12. The resin molding machine according to Claim 11, wherein an inner shape of said pot (12) is formed into a female-tapered shape in which diameter is made greater toward front open end.

13. The resin molding machine according to Claim 11,
wherein a plunger (13) in said pot (12) is
formed into a tapered shape in which diameter is
made smaller toward a front end.
14. A method of resin molding,
comprising the steps of:
clamping a member (20) to be molded by
molding dies (10a, 10b) having molding sections
including cavities (21); and
pressurizing resin melt by a pot (12) so as to
send the resin to the cavities (21),
characterised by the steps of:
fixing release film (30), which is capable of
easily peeling off from said molding dies (10a, 10b)
and resin for molding, on inner faces of the molding
sections and clamping faces, which are peripheral
faces of the molding sections, by a fixing mecha-
nism for fixing said release film (30) by sucking air;
and
clamping the member (20) to be molded by
said molding dies (10a, 10b) together with said
release film (30).
15. The method of resin molding according to Claim 14,
wherein resin supplied into said pot (12) is
tightly wrapped with wrapping film (44, 46), and
wherein an edge of the wrapping film (44,
46), which is overflowed from said pot (12), is over-
lapped with an edge of said release film (30) in a
resin path connecting said pot (12) and the cavity
(21).
16. The method of resin molding according to Claim 15,
wherein the edge of the wrapping film (44,
46), which has been set in said pot (12), is coin-
cided with a border between the cavity (21) and a
gate (10c).
17. The method of resin molding according to Claim 15,
wherein the edge of the wrapping film (44,
46), which has been set in said pot (12), is sepa-
rated away from a border between the cavity (21)
and a gate (10c), whereby the resin is capable of
adhering onto a surface of the member (20) to be
molded.
18. The method of resin molding according to Claim 14,
wherein the member (20) to be molded is a
dam-barless lead frame.
19. The method of resin molding according to Claim 15,
wherein the member to be molded is a lead
frame (20) having a gate window (20a), which is an
opening section corresponding to a gate (10c), and
wherein one of said molding dies (10a, 10b)
has a dam block (20c), which is capable of closing
the gate window (20a) when said molding dies
(10a, 10b) clamp the lead frame (20).
20. The method of resin molding according to Claim 14,
wherein the member to be molded is a chip-
size package (7), and
wherein wire patterns, which have been pro-
vided in edge sections of said chip-size package
(7), is molded.
21. Release film (30) for resin molding, which is fixed
on inner faces of molding sections of molding dies
(10a, 10b) and clamping faces thereof, which are
peripheral faces of the molding sections, by sucking
air,
characterized in that,
a transferring layer (60), which is capable of
being transferred onto a surface of resin molded, is
provided on a surface of said release film (30).

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG.7




FIG.8




FIG.9




FIG.10




FIG.11 A




FIG.11B




FIG.12 A




FIG.12B




FIG.13A




FIG.13B




FIG.14 A





FIG.14 B

FIG.15 A





FIG.15 B

FIG.16 A





FIG.16 B

FIG.17A




FIG.17B




FIG.18A




FIG.18B




FIG.20




FIG. 22




FIG. 21A




FIG. 19A




FIG. 21B




FIG. 19B

FIG.23




FIG.24




FIG. 25




FIG. 26




FIG. 27




FIG. 28




FIG. 29




FIG. 30




FIG.31




FIG.32




FIG.33




FIG. 34




FIG. 35




FIG.36




FIG.37




FIG. 38




FIG. 39




FIG. 40




FIG. 41




FIG. 42




FIG.43





FIG.44



EUROPEAN SEARCH REPORT

Application Number
EP 95 30 8258

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
P,X	EP-A-0 665 584 (3P LICENSING B V) 2 August 1995 * the whole document *	1,2, 14-18, 20,21	B29C45/02 H01L21/56 B29C33/68
X	--- PATENT ABSTRACTS OF JAPAN vol. 013 no. 500 (M-891) ,10 November 1989 & JP-A-01 202415 (MATSUDA SEISAKUSHO:KK) 15 August 1989, * abstract *	21	
Y	--- PATENT ABSTRACTS OF JAPAN vol. 010 no. 375 (M-545) ,13 December 1986 & JP-A-61 167515 (HITACHI LTD) 29 July 1986, * abstract *	1,2,4,14	
Y	--- PATENT ABSTRACTS OF JAPAN vol. 010 no. 375 (M-545) ,13 December 1986 & JP-A-61 167515 (HITACHI LTD) 29 July 1986, * abstract *	1,2,4,14	
A	--- PATENT ABSTRACTS OF JAPAN vol. 009 no. 294 (M-431) ,20 November 1985 & JP-A-60 131213 (NIPPON SEIKOSHO KK;OTHERS: 01) 12 July 1985, * abstract *	11,15-20	
X	--- PATENT ABSTRACTS OF JAPAN vol. 009 no. 294 (M-431) ,20 November 1985 & JP-A-60 131213 (NIPPON SEIKOSHO KK;OTHERS: 01) 12 July 1985, * abstract *	21	
A	--- PATENT ABSTRACTS OF JAPAN vol. 018 no. 461 (E-1597) ,26 August 1994 & JP-A-06 151490 (TOSHIBA CORP) 31 May 1994, * abstract *	1,11,14	TECHNICAL FIELDS SEARCHED (Int.Cl.6) B29C H01L
A	--- PATENT ABSTRACTS OF JAPAN vol. 014 no. 206 (M-0967) ,26 April 1990 & JP-A-02 045117 (MITSUBISHI ELECTRIC CORP) 15 February 1990, * abstract *	1,11,14	
		-/--	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 21 February 1996	Examiner Van Wallene, A
CATEGORY OF CITED DOCUMENTS		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 95 30 8258

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	PATENT ABSTRACTS OF JAPAN vol. 011 no. 238 (M-613) ,5 August 1987 & JP-A-62 051416 (SONY CORP) 6 March 1987, * abstract *	3,6-9	
A	--- PATENT ABSTRACTS OF JAPAN vol. 012 no. 061 (M-671) ,24 February 1988 & JP-A-62 207615 (FUJITSU LTD) 12 September 1987, * abstract *	3,6-9	
A	--- DE-A-38 11 814 (SIEMENS AG) 19 October 1989	12,13	
A	--- US-A-5 043 199 (KUBOTA AKIHIRO ET AL) 27 August 1991 -----	15	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
Place of search THE HAGUE		Date of completion of the search 21 February 1996	Examiner Van Wallene, A
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 01.82 (P04001)